



DongGuan Merrock Industry Co., Ltd

Add: Xiya Industrial park, Jiaolian community, Wanjiang District, Dongguan City, China
TEL No.: 0086-769-23291955 FAX No.: 0086-769-23152826
Lucy Luo 0086-18929453650 dgmerrock@hotmail.com www.stonefloorpolisher.com

MRK-24 fast curing agent construction

- 1) 50 # pads grinding uniformly (eg relatively uneven ground, we need to start from 30# grinding)
- 2) 150 # grinding (wet or dry both can)
- 3) 300 # grinding, rinsing and then cleaning up, when the ground reaches the dry state, spraying the curing agent, with a special mop drag back and forth, so that the curing agent applied evenly and kept moist state a period of time (40 minutes till 1 hours), at same time, it need to supplement some of the curing agent to keep the ground moist, so it would be more uniform curing
- 4) It is a normal phenomenon that the ground is white after fast hardener dry
- 5) When dry completely, after **five** hours, with # 500 pads to polish uniformly, then, clean, rinse with water the ground
- 6) When the ground is dry totally, dry polishing with 800 # by fast speed polishing machine
- 7) If you need to further improve, can choose # 1500 dry polishing from our factory one more time
- 8) If you need to make a mirror-like surface effect, choose our MRK-0 brightener



DongGuan Merrock Industry Co., Ltd

Add: Xiya Industrial park, Jiaolian community, Wanjiang District, Dongguan City, China
TEL No.: 0086-769-23291955 FAX No.: 0086-769-23152826
Lucy Luo 0086-18929453650 dgmerrock@hotmail.com www.stonefloorpolisher.com

MRK-20 curing agent construction

- 1) 50 # pads grinding uniformly (eg relatively uneven ground, we need to start from 30# grinding)
- 2) 150 # grinding (wet or dry both can)
- 3) 300 # grinding, rinsing and then cleaning up, when the ground reaches the dry state, spraying the curing agent, with a special mop drag back and forth, so that the curing agent applied evenly and kept moist state a period of time (40 minutes till 1 hours), at same time, it need to supplement some of the curing agent to keep the ground moist, so it would be more uniform curing
- 4) When dry completely, after **twelve** hours, with # 500 pads to polish uniformly, then, clean, rinse with water the ground
- 5) When the ground is dry totally, dry polishing with 800 # by fast speed polishing machine
- 6) If you need to further improve, can choose # 1500 dry polishing from our factory one more time
- 7) If you need to make a mirror-like surface effect, choose our MRK-0 brightener

Remark: could not mix MRK-20 and MRK-24, should operate individually for project. It needs proper way for ideal effect.



DongGuan Merrock Industry Co., Ltd

Add: Xiya Industrial park, Jiaolian community, Wanjiang District, Dongguan City, China
TEL No.: 0086-769-23291955 FAX No.: 0086-769-23152826
Lucy Luo 0086-18929453650 dgmerrock@hotmail.com www.stonefloorpolisher.com



The projects from our customers with our curing agent, polishing pads and our polishing machines with proper way